

**IN-MOLD DECORATING SHEET AND IN-MOLD  
DECORATED ARTICLE USING THE SAME**

Sub  
Spec  
(NE)

**5      Technical Field**

[0001]      The present invention relates to an in-mold decorating sheet, as well as an in-mold decorated article using the same, for use in decorating surfaces of molded products of three-dimensional shapes including: interior automotive trims such as a console box, center cluster, and switch base; exterior automotive trims such as side mudguard, bumper, wheel covers and braid; and component parts for household electrical appliances such as a refrigerator door and air-conditioner front panel.

**Background Art**

[0002]      A widely used method for decorating automotive trims and household electrical appliance parts as described above includes forming a pattern by performing colored coating, plating, or the like on a desired color and pattern, and thereafter applying an entire-surface overcoating for protection of the pattern. However, coating and plating have been problematic in terms of environmental hygiene.

[0003]      In contrast to this, as a method for decorating a surface without coating, there has been known an in-mold decorating method using an in-mold decorating sheet.

[0004]      This method includes setting an in-mold decorating sheet into an injection mold, clamping the mold, injecting a molten molding resin into a cavity of the mold, and allowing the molding resin to set, wherein the in-mold decorating sheet 61 is integrally bonded to a surface of a resin molded article 74, by which an in-mold decorated article is obtained (see Fig. 34).

**[0005]** The in-mold decorating sheet is, generally, composed of a pattern layer having a pattern, a substrate sheet serving for covering and protecting the pattern layer, and a backing sheet for protecting the decorating sheet against heat and pressure caused by the molding resin or serving as a pattern sheet by itself.

5 **[0006]** However, such in-mold decorating sheets as described above have had the following issues, respectively.

**[0007]** A first issue is that unless the in-mold decorating sheet is made from a material having certain properties, the in-mold decorating sheet could be neither three-dimensionally worked into a desired configuration nor processed for in-mold decorating.

10 **[0008]** That is, in a case where the in-mold decorating sheet is made from a material such as a pure ethylene-vinyl acetate film, there has been an issue that heat of molding resin injected during an injection molding process is applied to the in-mold decorating sheet and, additionally, the in-mold decorating sheet is stretched along the flow of the molding resin, leading to a break of the in-mold decorating sheet.

15 **[0009]** Also, in another case where the in-mold decorating sheet is made from a material having high heat resistance and low elongatability such as biaxially oriented polyethylene terephthalate, polyimide, polyether etherketone, polysulfone, polyethersulfone, polyetherimide, or polyamide-imide films, there has been an issue that it is difficult to work the in-mold decorating sheet into a three-dimensional configuration. In particular, the more  
20 deeply the in-mold decorating sheet is drawn, the more difficult it is to work the in-mold decorating sheet into a three-dimensional configuration.

**[0010]** Further, when the in-mold decorating sheet is made from a material having low rigidity, the in-mold decorating sheet becomes liable to collapse in its three-dimensional configuration after three-dimensional working of the in-mold decorating sheet, leading to a  
25 lowered configuration retainability. In such a case, there has been an issue that it becomes difficult to process an in-mold decorating sheet for trimming or in-mold decorating.

[0011] Therefore, it is an object of the present invention to provide an in-mold decorating sheet, as well as an in-mold decorated article using this in-mold decorating sheet, which in-mold decorating sheet is suited for working into a three-dimensional configuration without breaking due to heat of molding resin injected during an injection molding process, and which is superior in configuration retainability after working the in-mold decorating sheet into a three-dimensional configuration.

## **SUMMARY OF THE INVENTION**

[0012] In order to accomplish the above object, the present invention has the following constitutions.

[0013] According to a first aspect of the present invention, there is provided an in-mold decorating sheet having high three-dimensional workability for use in a manufacturing method of an in-mold decorated article. The method comprises setting an in-mold decorating sheet into a mold for in-mold decorating sheet injection-molding. After clamping the mold, molding resin is injected and allowed to cool and solidify, by which all or part of the in-mold decorating sheet is integrally bonded to a surface of the molding resin.

[0014] The in-mold decorating sheet comprises at least a substrate sheet and a backing sheet, exhibits a colored state, and has the following characteristic values:

(1) when a tensile test is carried out with a 10 mm wide test specimen of the in-mold decorating sheet fixed between a pair of chucks at a chuck-to-chuck distance of 5 mm, by applying a load at a constant rate of 500 mm/min to one end of the test specimen under an ambient temperature condition of 62 - 94°C, the test specimen exhibits a tensile load at breakage of not less than 23 gf;

(2) the in-mold decorating sheet changes in properties due to heat within a temperature range of 40 - 200°C; and when a tensile test is carried out with a 10 mm wide test specimen of the in-mold decorating sheet fixed between a pair of chucks at a chuck-to-chuck distance of 5 mm, by applying a load of 20 gf at a constant rate of 500 mm/min to one

end of the test specimen under an ambient temperature condition within a range from the temperature of property change to a temperature at which the in-mold decorating sheet is thermally decomposed, the test specimen exhibits a tensile elongation at breakage of not less than 130%.

5 [0015] According to a second aspect of the present invention, there is provided the in-mold decorating sheet according to the first aspect, wherein the manufacturing method of the in-mold decorated article comprises: after working the in-mold decorating sheet into a three-dimensional configuration, removing portions of the in-mold decorating sheet unnecessary for decorating by performing a trimming process; then setting the in-mold decorating sheet into the mold for injection-molding; and after clamping the mold, injecting molding resin and allowing the molding resin to be cooled and solidified, by which all or part of the in-mold decorating sheet is integrally bonded to a surface of the molding resin. When a tensile test is carried out with a 10 mm wide test specimen of the in-mold decorating sheet fixed between a pair of chucks at a chuck-to-chuck distance of 5 mm, by applying a load at a constant rate of 500 mm/min to one end of the test specimen under an ambient temperature condition of 25°C, a product of Young's modulus and a cube of thickness of the in-mold decorating sheet measured during the tensile test is not less than 1 kgfmm<sup>2</sup>.

15 [0016] According to a third aspect of the present invention, there is provided an in-mold decorating sheet according to the first or second aspect, wherein a pencil hardness value of the in-mold decorating sheet measured on one side thereof opposite to the side to be bonded to the molding resin is 3B - 2H.

20 [0017] According to a fourth aspect of the present invention, there is provided an in-mold decorating sheet according to the third aspect, wherein the substrate sheet is a film selected from among undrawn or lightly-drawn polyethylene terephthalate film, noncrystalline or low-crystalline polyester copolymer film, acrylic film, polycarbonate film, polypropylene film, 25 polybutylene terephthalate film, polystyrene film, polyurethane film, acrylonitrile butadiene-

styrene copolymer film, nylon film, polyvinyl chloride film, fluoric film, and cellulose acetate film.

[0018] According to a fifth aspect of the present invention, there is provided an in-mold decorating sheet according to any one of the first to fourth aspects, wherein a thickness of the in-mold decorating sheet is not less than  $250\text{ }\mu\text{m}$ , a thickness of the in-mold decorating sheet excluding thickness of the backing sheet is not more than  $200\text{ }\mu\text{m}$ , and color of the backing sheet is dark and falls within the following ranges in the CIE1976( $L^*a^*b^*$ ) color system:

$$9 \leq L^* \leq 75$$

$$-40 \leq a^* \leq 40$$

$$-60 \leq b^* \leq 30.$$

[0019] According to a sixth aspect of the present invention, there is provided an in-mold decorating sheet according to the fifth aspect, wherein the backing sheet is a film selected from among acrylic film, undrawn or lightly-drawn polyethylene terephthalate film, noncrystalline or low-crystalline polyester copolymer film, polypropylene film, polyethylene film, polystyrene film, fluoric film, polybutylene terephthalate film, methacryl-styrene copolymer film, acrylonitrile butadiene-styrene copolymer film, polycarbonate film, polyurethane film, nylon film, polyvinyl chloride film, and nitrocellulose film.

[0020] According to a seventh aspect of the present invention, there is provided an in-mold decorating sheet according to any one of the first to fifth aspects, wherein material of the backing sheet is a material which prevents vaporization and foaming.

[0021] According to an eighth aspect of the present invention, there is provided an in-mold decorating sheet according to any one of the first to seventh aspects, wherein a difference in shrinkage factor between the substrate sheet and the backing sheet is  $0/1000 - 8/1000$ .

[0022] According to a ninth aspect of the present invention, there is provided an in-mold decorating sheet according to the eighth aspect, wherein the substrate sheet is an acrylic film and the backing sheet is a polypropylene film containing olefin rubber and a filler material.

[0023] According to a tenth aspect of the present invention, there is provided an in-mold decorating sheet according to the ninth aspect, wherein when the olefin rubber is ethylene propylene rubber or ethylene-propylene-diene terpolymer, and its content is 20 - 150 parts by weight on the basis of 100 parts by weight of propylene resin.

5 [0024] According to an eleventh aspect of the present invention, there is provided an in-mold decorating sheet according to the ninth aspect, wherein when the filler material is talc, its content is 5 - 20 parts by weight on the basis of 100 parts by weight of propylene resin.

10 [0025] According to a twelfth aspect of the present invention, there is provided an in-mold decorating sheet according to any one of the first to eleventh aspects, wherein a pattern layer is formed between the substrate sheet and the backing sheet.

15 [0026] According to a thirteenth aspect of the present invention, there is provided a method for manufacturing an in-mold decorating sheet, wherein when the pattern layer of the in-mold decorating sheet defined in the twelfth aspect is formed, a carrier sheet, whose dimensional change rate under an ambient temperature of 90°C is within 0.6%, is laminated onto the substrate sheet, and the pattern layer is formed on a surface of the substrate sheet or the backing sheet opposite to the carrier sheet.

20 [0027] According to a fourteenth aspect of the present invention, there is provided a method for manufacturing an in-mold decorating sheet, wherein when the pattern layer of the in-mold decorating sheet defined in the twelfth aspect is formed, the pattern layer is formed on a carrier sheet whose dimensional change rate under an ambient temperature of 90°C is within 0.6%, and thereafter the substrate sheet is laminated onto the pattern layer side, and further the carrier sheet is separated and removed from the pattern layer so that the pattern layer is formed on a surface of the substrate sheet or the backing sheet.

**[0028]** According to a fifteenth aspect of the present invention, there is provided a method for manufacturing an in-mold decorating sheet according to the thirteenth or fourteenth aspect, wherein the carrier sheet is a biaxially oriented polyester film or a biaxially oriented polypropylene film.

5 **[0029]** According to a sixteenth aspect of the present invention, there is provided an in-mold decorating sheet according to any one of the first to fifteenth aspects, wherein a second pattern layer is formed between the backing sheet and the pattern layer.

**[0030]** According to a seventeenth aspect of the present invention, there is provided an in-mold decorating sheet according to the sixteenth aspect, wherein the substrate sheet is made  
10 from an easily vaporizable, foamable material, and the second pattern layer is made from a material that prevents vaporization and foaming.

**[0031]** According to an eighteenth aspect of the present invention, there is provided an in-mold decorating sheet according to the seventeenth aspect, wherein the second pattern layer is made from any material selected from among polyethylene resin, polypropylene resin, styrene resin, fire-retardant ABS resin, and thermoplastic polybutadiene resin.  
15

**[0032]** According to a nineteenth aspect of the present invention, there is provided an in-mold decorating sheet according to any one of the first to sixteenth aspects, wherein the backing sheet is a lamination of a plurality of sheets, and a difference in shrinkage factor between the substrate sheet and the sheet farthest from the substrate sheet is 0/1000 - 8/1000.

20 **[0033]** According to a twentieth aspect of the present invention, there is provided an in-mold decorating sheet according to the nineteenth aspect, wherein the backing sheet is formed from a plurality of polypropylene film layers, the substrate sheet is an acrylic film, and at least the propylene film layer farthest from the acrylic film contains olefin rubber and/or a filler material.

25 **[0034]** According to a twentifirst aspect of the present invention, there is provided an in-mold decorated article formed by a method comprising: setting into a mold the in-mold decorating sheet defined in any one of the first to twelvth and the fifteenth to twentieth

aspects; and after clamping the mold, injecting molding resin and allowing the molding resin to be cooled and solidified, by which all or part of the in-mold decorating sheet is integrally bonded to a surface of the molding resin.

## **5 BRIEF DESCRIPTION OF THE DRAWINGS**

[0035] These and other aspects and features of the present invention will become clear from the following description taken in conjunction with the preferred embodiments thereof with reference to the accompanying drawings, in which:

10 [0036] Fig. 1 is a sectional view showing one of the steps of a method for manufacturing an in-mold decorated article using an in-mold decorating sheet according to a first embodiment of the present invention;

[0037] Fig. 2 is a sectional view showing one of the steps of the method for manufacturing the in-mold decorated article using the in-mold decorating sheet according to the first embodiment;

15 [0038] Fig. 3 is a sectional view showing one of the steps of the method for manufacturing the in-mold decorated article using the in-mold decorating sheet according to the first embodiment;

[0039] Fig. 4 is a sectional view showing the in-mold decorated article obtained by the in-mold decorated article manufacturing method according to the first embodiment;

20 [0040] Fig. 5 is a sectional view showing the in-mold decorating sheet according to the first embodiment;

[0041] Fig. 6 is a sectional view showing the in-mold decorating sheet according to the first embodiment;

25 [0042] Fig. 7 is a sectional view showing the in-mold decorating sheet according to the first embodiment;

[0043] Fig. 8 is a sectional view showing the in-mold decorating sheet according to the first embodiment;



[0044] Fig. 9 is a sectional view showing a three-dimensionally worked in-mold decorating sheet to be used for the in-mold decorated article manufacturing method according to the first embodiment;

[0045] Fig. 10 is a sectional view showing one of the steps of the method for manufacturing the in-mold decorated article according to the first embodiment;

[0046] Fig. 11 is a sectional view showing one of the steps of the method for manufacturing the in-mold decorated article according to the first embodiment;

[0047] Fig. 12 is a perspective view showing a tensile tester for measuring tensile strength of an in-mold decorating sheet;

[0048] Fig. 13 is a plan view showing a portion for fixing a test specimen in the tensile tester;

[0049] Fig. 14 is a sectional view showing a portion for fixing a test specimen in the tensile tester;

[0050] Fig. 15 is a view showing a pencil scratching tester for measuring pencil hardness of a substrate film (substrate sheet) on a surface opposite to the surface on which the substrate film is to be bonded to molding resin;

[0051] Fig. 16 is a view showing integrating sphere type light transmittance measuring equipment to be used for determining a haze value of the substrate film (substrate sheet);

[0052] Fig. 17 is a sectional view showing an insert film as the in-mold decorating sheet according to the first embodiment of the present invention;

[0053] Fig. 18 is a sectional view showing one of the steps of a method for manufacturing an insert film as an in-mold decorating sheet according to a sixth embodiment of the present invention;

[0054] Fig. 19 is a sectional view showing one of the steps of the method for manufacturing the insert film as the in-mold decorating sheet according to the sixth embodiment of the present invention;

[0055] Fig. 20 is a sectional view showing one of the steps of the method for manufacturing the insert film as the in-mold decorating sheet according to the sixth embodiment of the present invention;

[0056] Fig. 21 is a sectional view showing one of the steps of a method for manufacturing an in-mold decorated article by using the insert film as the in-mold decorating sheet according to the sixth embodiment of the present invention;

[0057] Fig. 22 is a sectional view showing one of the steps of the method for manufacturing the in-mold decorated article by using the insert film as the in-mold decorating sheet according to the sixth embodiment of the present invention;

[0058] Fig. 23 is a sectional view showing one of the steps of the method for manufacturing the in-mold decorated article by using the insert film as the in-mold decorating sheet according to the sixth embodiment of the present invention;

[0059] Fig. 24 is a sectional view showing the in-mold decorated article obtained by using the insert film as the in-mold decorating sheet according to the sixth embodiment of the present invention;

[0060] Fig. 25 is a perspective view showing equipment for measuring tensile elongation at break of an insert film as an in-mold decorating sheet;

[0061] Fig. 26 is a plan view showing a portion for fixing a test specimen in the equipment for measuring tensile elongation at break of the insert film;

[0062] Fig. 27 is a sectional view showing the portion for fixing the test specimen in the equipment for measuring tensile elongation at break of the insert film;

[0063] Fig. 28 is a sectional view showing a decorating insert film as an in-mold decorating sheet according to a third embodiment of the present invention;

[0064] Fig. 29 is a sectional view showing the decorating insert film as the in-mold decorating sheet according to the third embodiment of the present invention;

[0065] Fig. 30 is a sectional view showing a method for manufacturing an in-mold decorated article using a trimmed decorating insert film as the in-mold decorating sheet according to the third embodiment of the present invention;

[0066] Fig. 31 is a sectional view showing a method for manufacturing the in-mold decorated article using the trimmed decorating insert film as the in-mold decorating sheet according to the third embodiment of the present invention;

[0067] Fig. 32 is a sectional view showing a trimming example of a decorating insert film as an in-mold decorating sheet;

[0068] Fig. 33 is a sectional view showing a trimming example of a decorating insert film as an in-mold decorating sheet;

[0069] Fig. 34 is a perspective view showing an example of an in-mold decorated article as an in-mold decorating sheet;

[0070] Fig. 35 is a sectional view showing a method for manufacturing an insert-molded decorated article using a trimmed decorating insert film according to the prior art;

[0071] Fig. 36 is a sectional view showing a method for manufacturing an insert-molded decorated article using a trimmed decorating insert film according to the prior art;

[0072] Fig. 37 is a sectional view showing a method for manufacturing an insert-molded decorated article using a trimmed decorating insert film according to the prior art;

[0073] Fig. 38 is a sectional view showing a preforming decorating sheet as an in-mold decorating sheet according to a fifth embodiment of the present invention;

[0074] Fig. 39 is a sectional view showing the preforming decorating sheet as the in-mold decorating sheet according to the fifth embodiment of the present invention;

[0075] Fig. 40 is a sectional view showing a preforming decorating sheet as an in-mold decorating sheet according to a fourth embodiment of the present invention;

[0076] Fig. 41 is a sectional view showing the preforming decorating sheet as the in-mold decorating sheet according to the fourth embodiment of the present invention;

[0077] Fig. 42 is a sectional view showing an in-mold decorating sheet according to a sixth embodiment of the present invention;

[0078] Fig. 43 is a sectional view showing the in-mold decorating sheet according to the sixth embodiment of the present invention;

5 [0079] Fig. 44 is a sectional view showing the in-mold decorating sheet according to the sixth embodiment of the present invention;

[0080] Fig. 45 is a sectional view showing a state of an embodiment in which a backing sheet adjacent to a substrate sheet is provided as a colored sheet of metallic red or the like with black pigment mixed therein;

10 [0081] Fig. 46 is a sectional view showing a state of an embodiment in which a backing sheet adjacent to a substrate sheet with a thickness of 200  $\mu\text{m}$  or less is provided as a colored sheet of metallic red or the like with black pigment mixed therein;

[0082] Fig. 47 is a sectional view showing a state of an embodiment in which a backing sheet is adjacent to a colored substrate sheet;

15 [0083] Fig. 48 is a sectional view showing a state of an embodiment in which a transparent colored pattern layer is set between two colorless, transparent substrate sheets with a total thickness of 200  $\mu\text{m}$  or less;

[0084] Fig. 49 is a graph showing a relationship between a tensile test curve at an environmental temperature of 25°C and a tensile test curve at temperatures at which the environmental temperature varies in nature due to heat;

20 [0085] Fig. 50 is a side view of a portion for fixing a test specimen in the pencil scratching tester of Fig. 15; and

[0086] Fig. 51 is a plan view of a portion for fixing a test specimen in the pencil scratching tester of Fig. 15.

25

## DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0087] Before the description of the present invention proceeds, it is to be noted that like parts are designated by like reference numerals throughout the accompanying drawings.

### 5 (First Embodiment)

[0088] Hereinbelow, a first embodiment of the present invention is described in detail with reference to the accompanying drawings.

[0089] Figs. 1 to 3 are sectional views each showing one of the steps of the method for manufacturing an in-mold decorated article using an in-mold decorating sheet according to a first embodiment of the present invention. Fig. 4 is a sectional view showing the in-mold decorated article obtained by the in-mold decorated article manufacturing method according to the first embodiment. Fig. 5 is a sectional view showing the in-mold decorating sheet according to the first embodiment of the present invention. Fig. 6 is a sectional view showing an in-mold decorating sheet according to the first embodiment of the present invention. Fig. 7 is a sectional view showing an in-mold decorating sheet according to the first embodiment of the present invention. Fig. 8 is a sectional view showing an in-mold decorating sheet according to the first embodiment of the present invention. Fig. 9 is a sectional view showing a three-dimensionally worked in-mold decorating sheet to be used for the in-mold decorated article manufacturing method according to the first embodiment of the present invention. Fig. 10 is a sectional view showing one of the steps of the method for manufacturing an in-mold decorated article according to the first embodiment of the present invention. Fig. 11 is a sectional view showing one of the steps of the method for manufacturing an in-mold decorated article according to the first embodiment of the present invention. Fig. 12 is a perspective view showing a tensile tester for measuring a tensile strength of an in-mold decorating sheet. Fig. 13 is a plan view showing a portion for fixing a test specimen in the tensile tester. Fig. 14 is a sectional view showing a portion for fixing a test specimen in the tensile tester. Fig. 15 is a view showing a pencil scratching tester for

measuring pencil hardness of a substrate film (substrate sheet) on one surface opposite to a surface on which the substrate film is bonded to molding resin. Fig. 16 is a view showing integrating sphere type light transmittance measuring equipment to be used for determining a haze value of the substrate film (substrate sheet). Fig. 50 is a side view of a portion for fixing a test specimen in the pencil scratching tester of Fig. 15. Fig. 51 is a plan view of a portion for fixing a test specimen in the pencil scratching tester of Fig. 15.

[0090] In the figures: 1 denotes a substrate film (substrate sheet); 1a a low-crystalline polypropylene film; 1b a low-crystalline or noncrystalline polypropylene film; 1c a high-crystalline propylene film; 2 a pattern layer; 3 an in-mold decorating sheet; 4 a movable die of an injection mold; 5 a stationary die of the injection mold to which the movable die 4 is clamped; 6 cavity-forming surfaces of the movable die 4 and the stationary die 5; 7 a clamp member for positioning and clamping the in-mold decorating sheet 3 to the movable die 4; 8 a gate portion of the stationary die 5; 9 vacuum suction holes formed in the movable die 4 and serving for vacuum-sucking the in-mold decorating sheet 3, which has been positioned to the movable die 4 by the clamp member 7, along an inner surface of the cavity of the movable die 4; 10 molding resin; 11 a cavity formed by the movable die 4 and the stationary die 5; 12 a resin-molded article; 13 a test specimen; 14 screws; 15 an upper chuck; 16 a lower chuck; 17 a movable member; 18 a pencil; 19 a test specimen mount; 20 a weight; 21 a test specimen; 22 a standard white plate; 23 a light trap; 24 a light source; 25 an integrating sphere; and 26 a light receiver.

[0091] The in-mold decorating sheet 3 (45 in Fig. 17) according to the first embodiment of the present invention is an in-mold decorating sheet 3 which includes a substrate film (substrate sheet) 1 (31 in Fig. 17) and a pattern layer 2 (32 in Fig. 17), and which is used in a method for manufacturing an in-mold decorated article. The method comprises: after working the in-mold decorating sheet 3 into a three-dimensional configuration as shown in Fig. 9, removing portions thereof unnecessary for decoration through a trimming process; then setting the in-mold decorating sheet 3 into the movable die

4 for injection molding as shown in Fig. 10; and after clamping the mold, injecting the molding resin 10, cooling and setting the injected molding resin 10 as shown in Fig. 11, thereby integrally bonding all or part of the in-mold decorating sheet 3 to a surface of the molding resin 10. The in-mold decorating sheet 3 (45 in Fig. 17) is made up so as to include  
5 at least a pattern layer 2 (32 in Fig. 17), a substrate film (substrate sheet) 1 (31 in Fig. 17) having the pattern layer 2 (32 in Fig. 17), and a backing sheet (33 in Fig. 17). Further, the in-mold decorating sheet 3 has characteristics as described in the following (1) - (3):

[0092] (1) As shown in Figs. 12 to 14, when a tensile test is carried out with a 10 mm wide test specimen 13 of the in-mold decorating sheet (3, 45) fixed between a pair of chucks  
10 15, 16 at a chuck-to-chuck distance of 5 mm, by applying a load at a constant rate of 500 mm/min to one end of the test specimen 13 under an ambient temperature condition of 62 - 94°C, the test specimen 13 exhibits a tensile load at breakage of not less than 23 gf.

[0093] (2) As shown in Figs. 12 to 14, when a tensile test is carried out with a 10 mm wide test specimen 13 of the in-mold decorating sheet 3 fixed between a pair of chucks 15,  
15 16 at a chuck-to-chuck distance of 5 mm, by applying a load at a constant rate of 500 mm/min to one end of the test specimen 13 under an ambient temperature condition of 25°C, a product of Young's modulus and a cube of a thickness of the in-mold decorating sheet 3 measured at the time of the tensile test is not less than 1 kgfmm<sup>2</sup>.

[0094] (3) The in-mold decorating sheet 3 changes in properties due to heat within a  
20 temperature range of 40 - 200°C; and as shown in Figs. 25 to 27, when a tensile test is carried out with a 10 mm wide test specimen 50 of the in-mold decorating sheet 45 fixed between a pair of chucks 52, 53 at a chuck-to-chuck distance of 30 mm, by applying a load of 20 gf at a constant rate of 100 mm/min to one end of the test specimen 50 under an ambient temperature condition within a range from the above temperature of property change  
25 to a temperature at which the in-mold decorating sheet 3 is thermally decomposed, the test specimen 50 exhibits a tensile elongation at breakage of not less than 130%.

[0095] The present inventor has discussed conditions under which the in-mold decorating sheet does not break during a molding process with respect to the foregoing first issue of the prior art. As a result, it is determined that the above characteristics (1) - (3) are necessary.

5 [0096] As a feature for the in-mold decorating sheet not to break during a molding process, as has been described as characteristic (1), as shown in Figs. 12 to 14, it was determined that when a tensile test is carried out with a 10 mm wide test specimen 13 of the in-mold decorating sheet 3 fixed between a pair of chucks 15, 16 at a chuck-to-chuck distance of 5 mm, by applying a load at a constant rate of 500 mm/min to one end of the test specimen 13 under an ambient temperature condition of 62 - 94°C, the test specimen 13 needs to exhibit a tensile load at breakage of not less than 23 kgf.

10 [0097] The reason why the in-mold decorating sheet 3 breaks during a molding process is that when heat of the molding resin 10 is applied to the in-mold decorating sheet 3 so that the in-mold decorating sheet 3 is stretched along the flow of the molding resin 10, the in-mold decorating sheet 3 does not have sufficient strength to limit deformation thereof so that breakage does not occur.

15 [0098] The injection temperature of the molding resin 10, in most cases, is 150 - 280°C. Therefore, first, in a case where (I) ethylene-vinyl acetate resin moldable at 150°C is injection-molded at the temperature, an in-mold decorating process was carried out with various types of in-mold decorating sheets, and the in-mold decorating sheets 3 were classified into those which broke during the molding process and those which did not break. Also, in another case where (II) polycarbonate resin moldable at 280°C is injection-molded at the temperature, a similar in-mold decorating process was carried out, and the in-mold decorating sheets 3 were classified into those which broke during the molding process and those which did not break. It is noted that as a result of measuring the temperatures of surfaces of the in-mold decorating sheets during the molding process, the temperature was

20

25



around 62°C in the case of (I), and around 94°C in the case of (II), due to transfer of heat of the injection molding resin.

[0099] Therefore, the reason why the temperature range was set to 62 - 94°C is that because an optimum injection temperature for most molding resins used for injection-molding is 150 - 280°C as described above, the in-mold decorating sheet is required to have such a strength as not to break even if the surface temperature of the in-mold decorating sheet is increased to 280°C due to transfer of heat of the resin to the in-mold decorating sheet. Further, some molding resins have optimum injection temperatures of higher than 280°C, and using such a resin would cause the in-mold decorating sheet to deteriorate regardless of how material of the in-mold decorating sheet is improved. Also, other molding resins have an optimum injection temperature of lower than 150°C, and using such a resin would cause the resulting in-mold decorated article to be insufficient in heat resistance performance.

[0100] Next, for each of the classified in-mold decorating sheets, a tensile test was carried out with a 10 mm wide test specimen 13 of the in-mold decorating sheet fixed between a pair of chucks 15, 16 at a chuck-to-chuck distance of 5 mm, by applying a load at a constant rate of 500 mm/min to one end of the test specimen 13 under an ambient temperature condition of 62°C in compliance with the measurement method defined in JIS K7127-1989 (see Figs. 12 to 14). As a result, test specimens of all of in-mold decorating sheets that had the same characteristics as those of the characteristic (1) above, and that broke during the in-mold decorating process exhibited tensile loads at breakage of less than 20 gf. Also, as a result of a similar tensile test carried out under an ambient temperature condition of 94°C (see Figs. 12 to 14), test specimens of all of in-mold decorating sheets that had the same characteristics as those of the characteristic (2) above, and that broke during the in-mold decorating process exhibited tensile loads at breakage of less than 23 gf. Therefore, it is determined that the in-mold decorating sheet is required to have a strength

of at least 23 gf or more tensile load at breakage in order to be prevented from breaking during a molding process.

[0101] It is noted here that the terms "ambient temperature" refer to a temperature of a test specimen in which the test specimen has been heated to the same temperature as that of the atmosphere of the test specimen.

[0102] The test specimen 13 is obtained by cutting an in-mold decorating sheet into a width of 10 mm and into such a size as can be provided for a tensile test using a pair of chucks 15, 16 at a chuck-to-chuck distance of 5 mm. The reason why the test specimen 13 is not large-sized is to prevent the test specimen 13 from softening and wrinkling all over under the above ambient temperatures before pulling the test specimen 13. Also, making the test specimen 13 into an excessively small size would cause measurement errors to increase. Because of these reasons, the test specimen 13 was made into as small a size as possible so that the measurement error is negligible, and then, the above size of the test specimen 13 was obtained. Referring to Figs. 12 to 14, the upper chuck 15 is fixed by a screw 14 while pinching an upper end of the test specimen 13. Also, the lower chuck 16 is fixed by a screw 14 while pinching a lower end of the test specimen 13. As shown in Figs. 12 to 14, while the upper chuck 15 is fixed to the tester, the lower chuck 16 is lowered at a rate of 500 mm/min by movable member 17, thereby causing a tensile force to act on the test specimen 13.

[0103] Further, the rate of 500 mm/min at which the test specimen 13 is pulled, has been selected as one that is the fastest within a measurable range for general tensile testers due to the fact that the rate at which the in-mold decorating sheet is stretched during actual three-dimensional working and injection molding processes is so fast that only a few types of equipment are capable of measurement with repeatability. Even though this rate is slower than rates at which the in-mold decorating sheet is stretched during working, measurement data actually do not change so much even when the setting of the pulling rate is changed, hence allowing sufficient simulation to be performed.

[0104] Also, since molding dies other than the injection molding dies are used in the three-dimensional working process as described in characteristic (2) above, there arises a need for a step of inserting the in-mold decorating sheet 3 into the injection molding dies 4, 5. As a result, the in-mold decorating sheet 3 is required to have rigidity.

5 [0105] This rigidity is proportional to Young's modulus of the in-mold decorating sheet 3 at an ambient temperature of 25°C and a cube of its thickness. For the in-mold decorating sheet 3 in this first embodiment of the present invention, the Young's modulus is defined by an initial modulus of elongation resulting when the above-described tensile test is performed with the width of the test specimen 13, the distance between the chucks 15, 16,  
10 and the rate as described above (that is, an initial modulus of elongation resulting when a tensile test is performed with a 10 mm wide test specimen 13 of the in-mold decorating sheet fixed between a pair of chucks 15, 16 at a chuck-to-chuck distance of 5 mm, by applying a load at a constant rate of 500 mm/min to one end of the test specimen 13 under an ambient temperature condition of 25°C by a measuring method complying with the measuring method  
15 of JIS K7127-1989 as shown in Figs. 12 to 14). As a result of performing detailed tests (see the following Table 1), it was determined that unless the product of Young's modulus of the in-mold decorating sheet and the cube of its thickness is at least 1 kgfmm<sup>2</sup>, it is impossible to punch the in-mold decorating sheet or to fulfill the mold inserting work. For more efficient work, it is necessary that the product of Young's modulus of the in-mold decorating  
20 sheet 3 and the cube of its thickness be 5 kgfmm<sup>2</sup> or more.

[0106]

Table 1:

Substrate sheet	Backing sheet	Young's modulus of in-mold decorating sheet	Thickness of in-mold decorating sheet	Product of Young's modulus and cube of thickness of in-mold decorating sheet at an ambient temperature of 25°C	Insert-ability
Acrylic, 0.05 mm	Polypropylene 0.18 mm	80 kgf/mm <sup>2</sup>	0.23 mm	0.97 kgfmm	x
Acrylic, 0.05 mm	Polypropylene 0.19 mm	80 kgf/mm <sup>2</sup>	0.24 mm	1.11 kgfmm	Δ
Acrylic, 0.05 mm	Polypropylene 0.30 mm	80 kgf/mm <sup>2</sup>	0.35 mm	3.43 kgfmm	Δ
Acrylic, 0.05 mm	Polypropylene 0.35 mm	80 kgf/mm <sup>2</sup>	0.40 mm	5.12 kgfmm	○ - ◎
Acrylic, 0.05 mm	Polypropylene 0.45 mm	80 kgf/mm <sup>2</sup>	0.50 mm	10.0 kgfmm	◎
Acrylic, 0.07 mm	ABS 0.12 mm	140 kgf/mm <sup>2</sup>	0.19 mm	0.96 kgfmm	x
Acrylic, 0.07 mm	ABS 0.13 mm	140 kgf/mm <sup>2</sup>	0.20 mm	1.12 kgfmm	Δ
Acrylic, 0.07 mm	ABS 0.28 mm	140 kgf/mm <sup>2</sup>	0.35 mm	3.78 kgfmm	Δ
Acrylic, 0.07 mm	ABS 0.33 mm	140 kgf/mm <sup>2</sup>	0.40 mm	8.96 kgfmm	◎
Acrylic, 0.07 mm	Polycarbonate 0.1 mm	180 kgf/mm <sup>2</sup>	0.17 mm	0.88 kgfmm	x
Polycarbonate, 0.07 mm	Polycarbonate 0.1 mm	210 kgf/mm <sup>2</sup>	0.17 mm	1.03 kgfmm	Δ
Acrylic, 0.07 mm	Polycarbonate 0.11 mm	180 kgf/mm <sup>2</sup>	0.18 mm	1.05 kgfmm	Δ
Polycarbonate, 0.07 mm	Polycarbonate 0.09 mm	210 kgf/mm <sup>2</sup>	0.16 mm	0.86 kgfmm	x

[0107] It was also found that, as described in characteristic (3) above, when a tensile test is performed according to the measuring method of JIS K7127-1989, the temperature at which the in-mold decorating sheet is changed in properties due to heat is within a range of 40 - 200°C, and that when as shown in Figs. 25-27, a tensile test is carried out with a 10 mm wide test specimen 50 of the in-mold decorating sheet fixed between a pair of chucks 52, 53 at a chuck-to-chuck distance of 30 mm, by applying a load of 20 gf at a constant rate of 100 mm/min to one end of the test specimen 50 under an ambient temperature condition within a range from the above temperature of property change to a temperature at which the in-mold decorating sheet is thermally decomposed, the test specimen 50 is required to exhibit a tensile elongation at breakage of not less than 130%. In Figs. 25 to 27, the upper chuck 52 is fixed by a screw 51 while pinching an upper end of the test specimen 50. Also, the lower chuck 53 is fixed by a screw 51 while pinching a lower end of the test specimen 50. As shown in Figs. 25 to 27, while the upper chuck 52 is fixed to the tester, the lower chuck 53 is lowered at a rate of 100 mm/min by a movable member 54, causing a tensile force to act on the test specimen 50.

[0108] The temperature at which properties change due to heat herein refers to a temperature at which Young's modulus at the temperature becomes at most 80% of Young's modulus that is exhibited under an ambient temperature of 25°C (see Fig. 49). It is noted that  $\theta_1$  is the gradient at the ambient temperature of 25°C, and  $\theta_2$  is the gradient at the temperature at which property change results from heat of the ambient temperature, where  $(80\% \text{ angle of } \theta_1) \geq \theta_2$ .

[0109] In order to allow an easy three-dimensional working of the in-mold decorating sheet, it is necessary that the in-mold decorating sheet be softened at least at a certain temperature, and that when loaded under a temperature higher than the certain temperature, the in-mold decorating sheet stretch without breaking. Therefore, the temperature range of property change due to heat is defined as 40 - 200°C.

[0110] The reason of this is that (I) with a material falling within a temperature range below 40°C, the in-mold decorating sheet is less resistant to heat so that the in-mold decorating sheet may peel from the decorated article due to temperature rises during summer; and that (II) with a material that is not thermally deformed even at 200°C, the in-mold decorating sheet requires too much time to be processed for three-dimensional working.

[0111] A further optimal temperature range for property change due to heat varies depending on the purpose of use. For example, for household electrical appliances such as refrigerators and air conditioners, because of their large product size and importance of three-dimensional workability, materials showing property change at temperatures of 40 - 160°C are preferably chosen. For applications to interior automotive trims, in which high heat resistance and deep three-dimensional workability are required, materials showing property change at temperatures of 60 - 150°C are preferably chosen.

[0112] The thickness of the in-mold decorating sheet (3, 45) is, preferably, within a range of 50 - 2000  $\mu\text{m}$ . With a thickness over 2000  $\mu\text{m}$ , the in-mold decorating sheet is inferior in moldability, so that the in-mold decorating sheet requires too much time to be worked into a three-dimensional configuration. With a thickness below 50  $\mu\text{m}$ , there occurs such molding failures as wrinkling of the in-mold decorating sheet during molding integration. Also, with a working sequence which includes: three-dimensionally working the in-mold decorating sheet; thereafter removing portions of the in-mold decorating sheet unnecessary for decorating by trimming; and then setting the resultant in-mold decorating sheet into an injection mold, most in-mold decorating sheets having a thickness of less than 250  $\mu\text{m}$  would not satisfy the condition described in characteristic (2) above.

[0113] More preferably, the thickness is within a range of 250 - 700  $\mu\text{m}$ . This is because thickness beyond 700  $\mu\text{m}$  would make it difficult to put the in-mold decorating sheet into a rolled state, and make it impossible to continuously feed and process the in-mold decorating sheet.

[0114] As the above description is based on the assumption that three-dimensional working is carried out within the movable die of the injection mold, there is a sequence, in the manufacturing process, which includes: setting of the in-mold decorating sheet into the injection mold and processing the sheet for three-dimensional working; and after molding and integration, trimming the in-mold decorating sheet. In this case, because there is no step for inserting the trimmed in-mold decorating sheet into the mold, it is not necessarily required for the sheet to have rigidity, such that the condition described in characteristic (2) above becomes unnecessary.

[0115] As a method for lamination of individual sheets for the in-mold decorating sheet, a heat lamination method, dry lamination method, and the like are available.

[0116] As required, an adhesion layer may preparatorily be formed on one surface of the backing sheet to be integrally bonded to the molding resin. Without the adhesion layer, the backing sheet layer basically serves as an adhesion layer, but the presence of an adhesion layer allows a firmer bonding to the molding resin to be attained. When the adhesion layer is formed, polyvinyl chloride - vinyl acetate copolymer resins, acrylic resins, urethane resins, or the like may appropriately be used.

[0117] Next, a method for manufacturing a resin molded article decorated with an in-mold decorating sheet is described.

[0118] First, an in-mold decorating sheet 3 is set by clamp member 7 to a surface of movable die 4, which is part of an injection mold.

[0119] A concrete example of the way the in-mold decorating sheet is set to the movable die 4 is as follows. A longer in-mold decorating sheet 3 is wound up on a roll shaft so as to be formed into a rolled state, and the resulting roll is placed at an upper portion of the movable die 4 so as to be movable integrally with the movable die 4. Then the in-mold decorating sheet 3, while being unwound from the roll, is passed between the movable die 4 in a retracted position and the stationary die 5 so as to be wound by a roll shaft of a film winding device which is set at a lower portion of the movable die 4 so as to be movable integrally with the movable die 4. As another example, a leaf-like in-mold decorating sheet

3 may be set to the surface of the movable die 4 by a robot or human hand (see Fig. 1). For the setting of the in-mold decorating sheet 3 onto the surface of the movable die 4, after the in-mold decorating sheet 3 is placed on the surface of the movable die 4, the position of the in-mold decorating sheet 3 relative to the surface of the movable die 4 is determined by a positioning sensor or the like, and the in-mold decorating sheet 3 may be pressed by the clamp member 7 to the surface of the movable die 4.

[0120] Subsequently, the in-mold decorating sheet 3 is set to the surface of the movable die 4, and thereafter, with the use of the vacuum suction holes 9 formed in the movable die 4, the in-mold decorating sheet 3 is vacuum-sucked along a recessed portion of the movable die 4 having the cavity-forming surface 6, by which the in-mold decorating sheet 3 is worked into a three-dimensional configuration along the recessed portion of the movable die 4 (see Fig. 2). A concrete example is a method which includes steps of: heating, and thereby softening, the in-mold decorating sheet 3 set to the surface of the movable die 4 by using a heating plate or the like inserted between the movable die 4 and the stationary die 5; closing the space between the recessed portion of the movable die 4 and the in-mold decorating sheet 3; and performing evacuation and vacuum suction through the vacuum suction holes 9 so that the in-mold decorating sheet 3 is put into close contact with the recessed portion of the movable die 4. During the process of working the in-mold decorating sheet into a three-dimensional configuration, or during the process of pressing and clamping of the in-mold decorating sheet 3 by the clamp member 7, trimming of the unnecessary portions of the in-mold decorating sheet 3 may be performed.

[0121] Instead of this method, before the in-mold decorating sheet 3 is set to the surface of the movable die 4, the in-mold decorating sheet 3 may preparatorily be worked into a desired configuration via a mold for three-dimensional working and molding other than the movable die 4 and stationary die 5, and also trimmed into a desired configuration (see Fig. 9), and then the three-dimensionally worked in-mold decorating sheet 3 is fitted into the recessed portion of the movable die (see Fig. 10). It is noted here that the three-dimensional



working refers to transforming the in-mold decorating sheet 3 from a planar state into a three-dimensional configuration. An example of a desired configuration is a configuration coincident with the cavity-forming surface 6 of the movable die 4 or stationary die 5. As possible methods for three-dimensional working the in-mold decorating sheet, there are a vacuum molding method, an air-pressure forming a method, a pressing method in which heated rubber is pressed against the in-mold decorating sheet, a press molding method, and the like. As possible methods for trimming the in-mold decorating sheet into a desired configuration, there are a Thomson punching method, a pressing method with dies, and the like. Examples of punching configurations are a line extending along the perimeter of a specified configuration, a hole of a specified configuration, and the like. In addition, the trimming process may be performed concurrently with the process of working the in-mold decorating sheet into a three-dimensional configuration.

[0122] Next, with the movable die 4 clamped to the stationary die 5, the molding resin 10 in a molten state is injected from the gate portion 8 of the stationary die into cavity 11 (see Figs. 3 and 11), and the molding resin 10 is solidified so that a resin molded article 12 is molded within the cavity 11 while the in-mold decorating sheet 3 is concurrently bonded integrally to a surface of the resin molded article 12.

[0123] Thereafter, the resin molded article 12 is removed from the movable die 4, and then unnecessary portions of the in-mold decorating sheet 3 bonded to the resin molded article 12 are removed (see Fig. 4). In the case where the in-mold decorating sheet 3 has preparatorily been trimmed into a desired configuration as described above, the step of removing the unnecessary portions of the in-mold decorating sheet 3 is unnecessary.

[0124] The movable die 4 and the stationary die 5, as the injection mold, are not particularly limited to the above embodiment. It is appropriate to use a mold which is made up of a movable die 4 and a stationary die 5 having a gate portion 8 for injecting the molding resin 10, where when the stationary die 5 and the movable die 4 are closed, a singularity or plurality of cavities 11 surrounded by the cavity-forming surfaces 6 of the stationary die 5

and the movable die 4 are formed. The in-mold decorating sheet 3 set within the cavities 11 formed by the movable die 4 and the stationary die 5 covers the cavity-forming surfaces 6. The recessed portion having a cavity-forming surface 6 may be formed in either the stationary die 5 or the movable die 4. A clamp member 7 for pressing and fixing the in-mold decorating sheet 3 around the recessed portion of the movable die 4 or the stationary die 5 may be provided.

**(Second Embodiment)**

[0125] Next, a second embodiment of the present invention is described. This second embodiment is intended to solve a second issue, i.e., prevention of damage.

[0126] As the second issue, there has been an issue that an outermost surface of the in-mold decorating sheet in the in-mold decorated article, i.e., a substrate sheet surface, may be easily damaged. It has been found that, for example, with polybutadiene resin or the like used as the material of the substrate sheet of the in-mold decorating sheet, although an in-mold decorated article is obtained during a manufacturing process, there is a high possibility that this article, when used as a component for assembly and working, would result in a defective product in terms of the substrate sheet surface due to claw marks caused by an assembling worker.

[0127] With respect to the second issue, the present inventor discussed what level of surface hardness is required in order to prevent high rates of defective products due to an assembling worker's claw traces being impressed on the substrate sheet surface.

[0128] As a result, it was determined that the in-mold decorating sheet should have a pencil hardness value of 3B - 2H as measured from a surface of the in-mold decorating sheet opposite to its surface to be bonded to the molding resin. That is, substrate sheets whose surface hardness does not reach a pencil hardness values of 3B, more specifically, in-mold decorating sheets made of polybutadiene film, were unusable.

[0129] Conversely, substrate sheets whose surface hardness is beyond a pencil hardness value of 2H, more specifically, in-mold decorating sheets made of UV-curing type urethane film, were evaluated. As a result, these in-mold decorating sheets, although processible for three-dimensional working and in-mold processing, were unusable, in terms of design, due to occurrence of numerous microcracks on the surface.

[0130] However, in the case where after the three-dimensional working and the in-mold processing are performed, substrate sheets are coated with a high-hardness UV-curing type urethane resin, there occurs no problem. In this case, substrate sheets are evaluated before their surfaces are coated.

[0131] A surface hardness measuring method is a method for determining surface hardness from presence or absence of a scratch by scratching a surface of a test specimen 27, which has been cut to a 150 mm X 70 mm size, with a pencil of a coating-dedicated pencil scratching tester (see Figs. 15, 50, 51) complying with JIS K 5401-1969, where a pencil hardness value is a pencil hardness obtained when the times the surface is scratched is less than two times out of five times of performing tests. Scratching is performed by pressing a pencil 18 against the test specimen 27 via a weight 20 at  $45 \pm 1$  degrees, and in this state, moving test specimen mount 19. In Figs. 50 and 51, reference numeral 19a denotes studs for fitting the test specimen 27 to the test specimen mount 19, and 19b denotes a test specimen stopper bar.

[0132] As a result, in-mold decorating sheets showing pencil hardness values of 3B or higher were almost never damaged even by human's assembling work using claws.

[0133] As a result of the test, it was found that in-mold decorating sheets having the above characteristic can be obtained by selecting, as the substrate sheet, undrawn or lightly-drawn polyethylene terephthalate film, noncrystalline or low-crystalline polyester copolymer film, acrylic film, polycarbonate film, polypropylene film, polybutylene terephthalate film, polystyrene film, polyurethane film, acrylonitrile butadiene-styrene copolymer film, nylon film, polyvinyl chloride film, fluoric film, cellulose acetate film, or the like.

[0134] Among others, acrylic film proved to be exceedingly superior in transparency and weatherability in addition to the above characteristic, and hence provided to be a film having high added value as a substrate sheet in terms of clarity improvement of pattern design as well as a protective function of a pattern layer.

5 [0135] Further, for films that can be controlled in the degree of crystallinity, such as polyethylene terephthalate film and polypropylene film, it is advisable to adjust the degree of crystallinity so that the hardness becomes 3B or higher.

[0136] However, even if the hardness falls within the above range, market complaints may occur in cases where the in-mold decorated article according to the second embodiment  
10 of the present invention is mounted in applications involving repeated hand contact by consumers.

[0137] As a countermeasure therefor, preferably, materials having a pencil hardness value of B - 2H are selected for interior automotive trims, and materials having a pencil hardness value of HB - 2H are selected for electrical appliances.

15 **(Third Embodiment)**

[0138] Next, a third embodiment of the present invention is described. This third embodiment is intended to solve a third issue, i.e., prevention of visibility of trimmed cross-section lines.

[0139] As the third issue, it can occur that cut end faces due to trimming of the in-mold decorating sheet to be integrated with the molding resin are not buried in the molding resin but exposed, resulting in an in-mold decorating sheet poor in design. That is, there has been an issue that if a cut end face of the in-mold decorating sheet is exposed on a surface of the in-mold decorated article, boundary lines between the in-mold decorating sheet and its peripheral molding resin surface become noticeable, resulting in an in-mold decorating  
20 sheet which is so poor in design as to make it apparent that the in-mold decorating sheet is in-mold-decorated.  
25

[0140] With respect to this third issue, the in-mold decorating sheet according to the third embodiment of the present invention is so constituted that a thickness of the in-mold decorating sheet excluding a thickness of the backing sheet is not more than 200  $\mu\text{m}$ , and that color of the backing sheet is dark and falls within the following ranges in the CIE1976(L\*a\*b\*) color system:

$$9 \leq L^* \leq 75$$

$$-40 \leq a^* \leq 40$$

$$-60 \leq b^* \leq 30$$

More specifically, in the third embodiment, as shown in Figs. 28 and 29, the thickness of in-mold decorating sheet 61 excluding the thickness of a backing sheet 66 is not more than 200  $\mu\text{m}$ , and the color of the backing sheet 66 is a dark color falling within the following ranges in the CIE1976L\*a\*b\* color system:

$$9 \leq L^* \leq 75$$

$$-40 \leq a^* \leq 40$$

$$-60 \leq b^* \leq 30$$

[0141] The reason why the color of the backing sheet 66 is limited like this is as follows.

[0142] During a trimming process using a die press having a sharp blade 70, the in-mold decorating sheet 61 is not cut fully perpendicularly to a surface thereof, and a cut end face 67 of the in-mold decorating sheet 61 is angled relative to front-and-rear surfaces of the in-mold decorating sheet 61 (see Fig. 32). Also in the case where a trimming process by laser cutting is performed, if the in-mold decorating sheet 61 has been three-dimensionally worked into a drawing configuration by preforming a process before the trimming, then a laser beam 71 is irradiated in a constant direction so that the cut end face 67 is angled relative to front-and-rear surfaces of the in-mold decorating sheet 61 (see Fig. 33). In the case where molding resin is injected into a mold 72 with that a space formed between an inner wall of the mold 72, along which the in-mold decorating sheet 61 is set, and the cut end face 67 of the in-mold

decorating sheet 61 angled relative to this inner wall (see Fig. 35), it may occur that the cut end face 67 of the in-mold decorating sheet 61 is pressed against the inner wall of the mold 72 by pressure 73 of the molding resin (see Fig. 36), or that molding resin 69 does not enter into the space (see Fig. 37).

5 [0143] Generally, the molding resin 69 to be used for interior automotive trims, in many cases, is black or other similar colors. As a result, most of light is absorbed at a surface where the molding resin 69 is exposed, resulting in less reflection. In contrast to this, the in-mold decorating sheet 61 has the cut end face 67 formed rough by a cutting process, causing the light to be scattered, with the result that the in-mold decorating sheet 61 is poor in visual  
10 transparency as its rear is viewed from the cut end face 67. Also, a cut end face 67 of a second pattern layer 68, which is similar in color to the cut end face 67 of a pattern layer 63 or the ground of the pattern layer 63, is brighter than the molding resin. As a result, in comparison with the surface where the molding resin is exposed, reflected light (or color) of the entire cut end face of the in-mold decorating sheet 61 alone is conspicuous.

15 [0144] Therefore, in order that the reflected light (or color) of the entire cut end face 67 of the in-mold decorating sheet 61 becomes inconspicuous, the backing sheet layer 66 of the in-mold decorating sheet 61 is provided in black or some other similar color, and moreover, layers other than the backing sheet 66 (i.e., layers including a transparent resin film 62 serving as a substrate film, and pattern layer 63 having a grain duct layer 64 and a  
20 ground layer 65 in Fig. 28; layers including a transparent resin film 62 serving as a substrate film, pattern layer 63 having a grain conductor layer 64 and a ground layer 65, and a second pattern layer 68 in Fig. 29) are formed so as to have a thickness of less than 200  $\mu\text{m}$ , by which reflection at the entire cut end face 67 of the in-mold decorating sheet 61 is reduced.

[0145] With the use of the in-mold decorating sheet 61 having the above constitution,  
25 an insert-molded decorated article can be obtained by the following method.

[0146] First, an in-mold decorating sheet 61 is fixed to a preforming die, having a recessed portion for deep drawing, by virtue of a clamp or the like, and then the in-mold decorating sheet 61 is heated and softened by a heat source and further put into close contact with the surface of the preforming die by vacuum suction effected from the preforming die side. Next, with the vacuum suction released, the in-mold decorating sheet 61 is removed from the preforming die. Next, unnecessary portions of the in-mold decorating sheet are trimmed, by which a desired three-dimensionally worked in-mold decorating sheet 61 is obtained. Next, the three-dimensionally worked in-mold decorating sheet 61 is inserted into a cavity die having a recessed portion for deep drawing and fixed in the cavity die. Next, the cavity die and a core die of injection mold 72 are clamped together, thereby forming a closed space between the in-mold decorating sheet 61 and the core die. Molten molding resin 69 is injected into this space (see Figs. 30 and 31), and after allowing the resin to be cooled, the cavity die and the core die are opened, by which a decorated insert-molded article in which the in-mold decorating sheet 61 and the molding resin 69 have been integrated together can be obtained. This decorated insert-molded article has a blackish end face of a reinforcement sheet, i.e. the backing sheet 66, after the trimming of the in-mold decorating sheet 61, and the total thickness of the other laminations is not more than 200  $\mu\text{m}$ . Thus, lines of the cut end face 67 of the in-mold decorating sheet 61, even if exposed, are inconspicuous, and the decorated insert-molded article is preferable in terms of design.

[0147] In-mold decorating sheets, in which the color of the backing sheet 66 is out of the aforementioned range and in which the thickness of the layers other than the backing sheet 66 is not less than 200  $\mu\text{m}$ , were tested with the thickness and color of the backing sheet 66 changed in various ways. Test results show that reflected light (or color) of the entire cut end face of the in-mold decorating sheet is conspicuous as shown in the following

[0148]

Table 2:

Color of backing sheet			Thickness of in-mold decorating sheet ( $\mu\text{m}$ )	Thickness of backing sheet ( $\mu\text{m}$ )	Effect on prevention of visibility of trimming cross- section lines
L*	a*	b*			
40	0	-15	250	50	○ - Δ
9	-40	-60	250	50	Δ
75	40	30	250	50	Δ
40	0	-15	250	70	⊙
9	-40	-60	250	70	Δ
75	40	30	250	70	Δ
8	0	-15	250	70	x
76	0	-15	250	70	x
40	-41	-15	250	70	x
40	41	-15	250	70	x
40	0	-61	250	70	x
40	0	31	250	70	x
40	0	-15	700	500	○
9	-40	-60	700	500	Δ
75	40	30	700	500	Δ
40	0	-15	700	550	⊙
9	-40	-60	700	550	○ - Δ
75	40	30	700	550	○ - Δ
8	0	-15	700	550	x - Δ
76	0	-15	700	550	x - Δ
40	-41	-15	700	550	x - Δ
40	41	-15	700	550	x - Δ
40	0	-61	700	550	x - Δ
40	0	31	700	550	x - Δ
40	0	-15	2000	1800	⊙
9	-40	-60	2000	1800	Δ
75	40	30	2000	1800	Δ
40	0	-15	2000	1850	⊙
9	-40	-60	2000	1850	○
75	40	30	2000	1850	○
8	0	-15	2000	1850	x - Δ
76	0	-15	2000	1850	x - Δ
40	-41	-15	2000	1850	x - Δ
40	41	-15	2000	1850	x - Δ
40	0	-61	2000	1850	x - Δ
40	0	31	2000	1850	x - Δ



[0149] (2) Material of the backing sheet 66 should be one which, when formed into the in-mold decorating sheet 61, satisfies conditions that the in-mold decorating sheet 61 has the characteristics (1) - (3) above, that a pencil hardness value as measured from one surface of the in-mold decorating sheet 61 opposite to the surface to be bonded to the molding resin is 3B - 2H, and that the substrate sheet 62 is selected from among undrawn or lightly-drawn polyethylene terephthalate film, noncrystalline or low-crystalline polyester copolymer film, acrylic film, polycarbonate film, polypropylene film, polybutylene terephthalate film, polystyrene film, polyurethane film, acrylonitrile butadiene-styrene copolymer film, nylon film, polyvinyl chloride film, fluoric film, or cellulose acetate film.

[0150] Material for the backing sheet 66 is exemplified by undrawn or lightly-drawn polyethylene terephthalate film, noncrystalline or low-crystalline polyester copolymer film, polypropylene film, polyethylene film, polystyrene film, fluoric film, polybutylene terephthalate film, methacryl-styrene copolymer film, acrylonitrile butadiene-styrene copolymer film, polycarbonate film, polyurethane film, nylon film, polyvinyl chloride film, nitrocellulose film, or the like.

[0151] However, in the case where the substrate sheet 62 is made of an easily vaporizable, foamable material, there may arise an issue that the in-mold decorating sheet 61 has an orange-peel surface even if the backing sheet 66 is made of one of the above materials. This issue and the manner by which it is resolved are described below.

#### **(Fourth Embodiment)**

[0152] Next, a fourth embodiment of the present invention is described. This fourth embodiment is intended to solve a fourth issue, i.e., prevention of occurrence of an orange-peel state.

[0153] As the fourth issue, there has been a tendency that during a process of forming a desired configuration by vacuum molding, moisture content in sheet material vaporizes and foams due to heat during the vacuum molding so that a surface of an in-mold decorating sheet exhibits an orange peel state, resulting in impaired design and hence a defective article.

**[0154]** In such a case, vaporizable/foamable components contained in backing sheet material are often the cause of acceleration toward generation of an orange-peel surface. Therefore, it is preferable to select a material having a lower content of such components (anti-vaporization/foaming material).

5 **[0155]** That is, with respect to the fourth issue, the in-mold decorating sheet according to the fourth embodiment of the present invention is so constituted that the backing sheet is made of a material which prevents vaporization and foaming. More specifically, as shown in Figs. 40 and 41, backing sheet 104 is made of a material which prevents vaporization and foaming. It is noted that reference numeral 101 denotes a substrate sheet, 102 denotes a  
10 pattern layer, and 103 denotes an ABS film for reinforcing adhesion to a molding resin.

**[0156]** More specifically, because the vaporizable/foamable component is often moisture, the backing sheet 104 is preferably made of a material having as low a coefficient of water absorption as possible (specifically, at least 0.5% or lower, preferably 0.2% or lower).

15 **[0157]** Such a material is exemplified by undrawn or lightly-drawn polyethylene terephthalate film, noncrystalline or low-crystalline polyester copolymer film, polypropylene film whose coefficient of water absorption is 0.03% or lower, polyethylene film whose coefficient of water absorption is 0.01% or lower, polystyrene film whose coefficient of water absorption is 0.07% or lower, fluoric film whose coefficient of water absorption is  
20 0.03% or lower, polybutylene terephthalate film whose coefficient of water absorption is 0.8% or lower, methacryl-styrene copolymer film whose coefficient of water absorption is 1.5% or lower, fire retardant acrylonitrile butadiene-styrene copolymer film whose coefficient of water absorption is 0.9% or lower, polycarbonate film whose coefficient of water absorption is 0.5% or lower, polyurethane film whose coefficient of water absorption  
25 is 1% or lower, polyvinyl chloride film whose coefficient of water absorption is 0.1% or lower, or the like.

**(Fifth Embodiment)**

[0158] Next, a fifth embodiment of the present invention is described. This fifth embodiment is intended to solve a fifth issue, i.e., prevention of warpage.

[0159] As the fifth issue, there has been an issue that if material of a substrate sheet and material of a backing sheet largely differ from each other in terms of a shrinkage factor (for example, concretely, in the case where the substrate sheet is an acrylic film (with a shrinkage factor of around 5/1000) and the backing sheet is an ordinary polypropylene film (with a shrinkage factor of around 15/1000)), then there occurs warpage of the in-mold decorating sheet after a three-dimensional working process due to the difference between the shrinkage factors, thereby making it difficult to fulfill trimming and injection molding decoration processes.

[0160] With respect to this fifth issue, the in-mold decorating sheet of the fifth embodiment of the present invention is so constituted that the difference in shrinkage factors between the substrate film and the backing sheet is 0/1000 - 8/1000, or that the backing sheet is a lamination of a plurality of sheets while the difference in shrinkage factors between the substrate sheet and the sheet of the backing sheet that is farthest from the substrate sheet is 0/1000 - 8/1000.

[0161] That is, the in-mold decorating sheet is so constituted that either the substrate sheet or the backing sheet of the in-mold decorating sheet is modified so that the difference in shrinkage factors between the substrate sheet and the backing sheet is 0/1000 - 8/1000.

[0162] In most cases, it is easier to accomplish this difference between the shrinkage factors by applying an additive material to the sheet having the larger shrinkage factor. As a concrete example, as shown in Fig. 38, in the case of an in-mold decorating sheet in which the substrate sheet is an acrylic film 81 and the backing sheet is a polypropylene film 83, it is recommendable to modify the polypropylene film, which has the larger molding shrinkage factor. It is noted that reference numeral 82 denotes a pattern layer.

[0163] That is, as shown in Fig. 38, olefin rubber 84 and a filler material 85 are contained in the polypropylene film 83 so that molding shrinkage is suppressed. As a mechanism therefor, it could be considered that the rubber 84 and the filler material 85, when contained, cause polymer chains of the polypropylene resin deprived of degree of freedom, thereby lessening space that allows shrinkage in the polypropylene resin.

[0164] More specifically, the olefin rubber is exemplified by EPM (ethylene propylene rubber), EPDM (ethylene-propylene-diene terpolymer), TPE (thermoplastic elastomer), and EVA (ethylene-vinyl acetate). The filler material is exemplified by talc and calcium carbonate as well as by titanium oxide, aluminum hydroxide, ferrite, carbon fiber, glass fiber, silica, mica, carbon black, clay, alumina, wood meal, felt, or the like.

[0165] During a process of cooling a heated sheet, the larger the content of olefin rubber and filler material, the larger the effect of suppressing gradual shrinkage of the polypropylene film. On the other hand, as the content of the olefin rubber increases, the polypropylene film becomes softer and softer so that the in-mold decorating sheet lowers in rigidity. Further, as the content of the filler material increases, the filler material becomes more and more likely to separate from the polypropylene film surface during a vacuum molding process, making the polypropylene film surface into a recessed-and-projected pattern. This recessed-and-projected pattern affects the acrylic film, causing the in-mold decorating sheet to be degraded in design.

[0166] As a result of a detailed test, it is determined that the contents of the olefin rubber and the filler material are conditioned by the following proper ranges.

[0167] In the case where EPM or EPDM was used as the olefin rubber, the proper range for the content of the olefin rubber was determined to be 20 - 150 parts by weight on the basis of 100 parts by weight of propylene resin. Also, in the case where talc was used as the filler material, the proper range for the content of the filler material was determined to be 5 - 20 parts by weight on the basis of 100 parts by weight of propylene resin. Further,

the best proper range for both was found to be 50 - 100 parts by weight of EPM or EPDM and 10 - 15 parts by weight of talc on the basis of 100 parts by weight of propylene resin.

[0168] In addition, as another embodiment, in the event that some failure occurs due to excessive addition of the olefin rubber or the filler material, as shown in Fig. 39, the polypropylene film 83 is formed from a lamination of a plurality of polypropylene film layers 91, 92, wherein

(1) as one method, the olefin rubber and the filler material are contained only in the polypropylene film layer that is farther from the acrylic film, and as another method, (2) while the polypropylene film layer that is the closer to the acrylic film has a smaller content of the olefin rubber and the filler material, the other polypropylene film layer that is farther from the acrylic film has a larger content of the olefin rubber and the filler material.

[0169] The reason for this is that because the polypropylene film layer closer to the acrylic film has a smaller content of the olefin rubber, rigidity of a decorating film as a whole is maintained, and yet because the content of the filler material is also small, the filler material is less likely to separate from the polypropylene film surface because of heat during a preforming process, where the filler material, even if separated, would be intercepted by the polypropylene film layer that is closer to the acrylic film and would not reach the acrylic film.

[0170] In this case, preferably, the polypropylene film layer closer to the acrylic film is made larger in film thickness, while the polypropylene film layer farther from the acrylic film (i.e., the polypropylene film layer forming an outermost layer) is made smaller in film thickness. In addition, the polypropylene film layer closer to the acrylic film also includes a polypropylene film layer that is in direct contact with the acrylic film. As to the reason for this, generally, there is a tendency that the larger the film thickness, the smaller the shrinkage. Therefore, by the polypropylene film layer closer to the acrylic film being larger being film thickness, any shrinkage of the polypropylene film layer farther from the acrylic film can have less effect on the acrylic film.

[0171] The film thickness of the polypropylene film layer farther from the acrylic film (i.e., the polypropylene film layer forming the outermost layer) is, preferably, within a range from a film thickness similar to that of the acrylic film to twice this thickness.

[0172] As to the reason for this, generally, the polypropylene film layer, even if olefin rubber and filler material are contained therein, does not exhibit so small a shrinkage factor as does the acrylic film. Therefore, unless the polypropylene film layer is larger in film thickness than the acrylic film, the in-mold decorating sheet as a whole would be warped toward the polypropylene film layer side. With the polypropylene film layer being at least twice as thick as the acrylic film, there is no substantial difference between their shrinkage factors.

[0173] As to the content of the filler material to be contained in the polypropylene film layer farther from the acrylic film (i.e., the polypropylene film layer forming the outermost layer), its proper amount is 10 - 30 parts by weight on the basis of 100 parts by weight of propylene resin. As to the reason for this, if 30 or more parts by weight of the filler material is contained, the polypropylene film layer would become not only harder to mold into a three-dimensional configuration during a preforming process, but also more difficult to put into close contact with the molding resin (or adhesion layer). Meanwhile, with 10 or less parts by weight of the filler material, a shrinkage suppression effect would be insufficient so that the entire in-mold decorated article would be warped toward the polypropylene film layer side.

**(Sixth Embodiment)**

[0174] Next, a sixth embodiment of the present invention is described. This sixth embodiment is intended to solve a sixth issue, i.e., an improvement in registering accuracy of a pattern.

[0175] As the sixth issue, there has been an issue that since any of the sheet layers of a three-dimensionally workable in-mold decorating sheet tends to be deformed by a printing machine's tensile force or drying heat to be applied during formation of a pattern layer, the

in-mold decorating sheet is applicable only to patterns having less strict registering accuracy such as grain patterns. If these sheet layers are made from a too highly heat-resistant material, the sheets become lower in elongation property so that the sheets can no longer be worked into a three-dimensional configuration. Because of this issue, it is inevitably required to select a material which is relatively low in heat resistance. However, in the case where a material of low heat resistance is selected, registering errors are more likely to occur during printing and drying process, disadvantageously.

[0176] With respect to this sixth issue, the in-mold decorating sheet of the sixth embodiment of the present invention is so constituted that, as shown in Figs. 17 to 20, for the formation of pattern layer 32, a carrier sheet 34, whose dimensional change rate under an ambient temperature of 90°C is within 0.6%, is laminated onto substrate sheet 31, and pattern layer 32 is formed on a surface of the substrate sheet 31 or the backing sheet 33 opposite to the carrier sheet 34; or that for the formation of the pattern layer 32, the pattern layer 32 is formed on a carrier sheet 34 whose dimensional change rate under an ambient temperature of 90°C is within 0.6%, and thereafter, the substrate sheet 31 is laminated onto the pattern layer side and further the carrier sheet 34 is separated and removed from the pattern layer 32, by which the pattern layer 32 is formed on the surface of the substrate sheet 31 or the backing sheet 33.

[0177] The pattern layer 32, which is purposed to express characters, graphics, symbols, and the like on a surface of the in-mold decorated article, or to express a colored surface, is formed between the substrate sheet 31 and the backing sheet 33.

[0178] The pattern may be all-over solid in silver metallic color or the like, or may be one having a wood grain pattern or a stone grain pattern or the like in a single color or multiple colors. Further, the pattern may be a lamination of a transparent yellow all-over solid or pattern layer and, a silver metallic all-over solid or pattern layer to represent a gold all-over solid or pattern layer.

[0179] However, in the case of black-, metallic-color based all-over solid decoration or the like, since the decoration can be achieved by toning the color of the backing sheet, the pattern layer may be omitted.

[0180] The pattern layer 32 comprises at least one layer selected from a group consisting of a pigment ink layer composed of pigment and resin binder, a bright pigment layer composed of pearl pigment and resin binder, and a dye ink layer composed of dye and resin binder. The pattern layer 32 is formed by employing general-purpose printing devices (gravure, offset, screen) or by roll coating, reverse coating, lip coating, or the like.

[0181] Also, the pattern layer 32 may be a metallic thin film layer or a combination of a metallic thin film layer and a print layer. The metallic thin film layer is formed by a vacuum deposition process, sputtering process, ion plating process, plating process, or the like. Metals such as aluminum, nickel, gold, platinum, chromium, iron, copper, tin, indium, silver, titanium, lead, or zinc, or their alloys or compounds, are used depending on the metallic luster color to be expressed.

[0182] However, with patterns to which high registering accuracy is required as in the sixth issue described before, there is an issue that registering errors are more likely to occur during the printing and drying process.

[0183] In such a case, for the formation of the pattern layer 32, a carrier sheet 34, whose dimensional change rate under an ambient temperature of 90°C is within 0.6%, is laminated onto the substrate sheet 31, and the pattern layer 32 is formed on a surface of the substrate sheet 31 or the backing sheet 33 opposite to the carrier sheet 34; or for the formation of the pattern layer 32, the pattern layer 32 is formed on a carrier sheet 34 whose dimensional change rate under an ambient temperature of 90°C is within 0.6%, and thereafter, the substrate sheet is laminated onto the pattern layer side and further the carrier sheet 34 is separated and removed, by which the pattern layer 32 is formed on the surface of the substrate sheet 31 or the backing sheet 33. That is, it is appropriate that (1) the carrier sheet 34 having a high dimensional stability with regard to heat is laminated onto the



substrate sheet 31, and then the pattern layer 32 is printed and formed (see Fig. 42); or that (2) the pattern layer 32 is printed and formed on the carrier sheet 34, and then the pattern layer 32 is transferred to the substrate sheet 31.

[0184] In more detail, a composite film formed from a lamination of the carrier sheet 34 and the substrate sheet 31 is used as an original fabric, the pattern layer 32 is formed on a surface of the substrate sheet 31 on one side opposite to the carrier sheet 34, and thereafter the carrier sheet 34 is separated and removed from the substrate sheet 31. After this, the backing sheet 33 is laminated.

[0185] Otherwise, the pattern layer 32 is formed on a surface of the substrate sheet 31 on one side opposite to the carrier sheet 34, and thereafter the backing sheet 33 is laminated onto the pattern layer side of the substrate sheet 31. Therefore, the carrier sheet 34 is separated and removed from the substrate sheet 31.

[0186] Alternatively, the following operations may be performed. As shown in Fig. 18, with another carrier sheet 34 used as an original fabric, the pattern layer 32 is formed on a surface of the carrier sheet 34, thereafter the substrate sheet 31 is stacked and laminated onto the pattern layer side, and thereafter, as shown in Fig. 19, the carrier sheet 34 is separated and removed from the pattern layer 32, by which the pattern layer 32 is transferred to the substrate sheet 31. After this, as shown in Fig. 20, the backing sheet 33 is laminated onto the pattern layer side of the substrate sheet 31, by which an in-mold decorating sheet 45, in which the pattern layer 32 is placed between the substrate sheet 31 and the backing sheet 33, is formed (see Fig. 17).

[0187] Further, the following operations may also be performed. With another carrier sheet 34 used as an original fabric, the pattern layer 32 is formed on a surface of the carrier sheet 34, the backing sheet 33 is stacked and laminated onto the pattern layer side, and thereafter the carrier sheet 34 is separated and removed from the pattern layer 32, by which the pattern layer 32 is transferred to the backing sheet 33. After this, the substrate sheet 31 is laminated onto the pattern layer side of the backing sheet 33.

[0188] Further, the following operations may also be performed. As shown in Fig. 42, with another carrier sheet 34 used as an original fabric, the substrate sheet 31 is laminated onto a surface of the carrier sheet 34, the pattern layer 32 is formed on one side of the substrate sheet 31 opposite to the carrier sheet 34, and further as shown in Fig. 43, the backing sheet 33 is laminated onto the pattern layer 32. Thereafter, the carrier sheet 34 is separated and removed from the substrate sheet 31, by which an in-mold decorating sheet 45, in which the pattern layer 32 is placed between the substrate sheet 31 and the backing sheet 33, is formed.

[0189] As the carrier sheet 34, one whose dimensional change rate under an ambient temperature of 90°C is within 0.6%, and which is high in tensile strength and superior in surface smoothness, is used.

[0190] As a carrier sheet 34 whose dimensional change rate under an ambient temperature of 90°C is within 0.6%, since the sheet is to be separated and removed during a manufacturing process of the in-mold decorating sheet, it is preferable to use inexpensive biaxially oriented polyester films or biaxially oriented polypropylene films.

[0191] As to setting of the ambient temperature to 90°C, an atmospheric temperature inside a drying unit installed in a normal multicolor printing machine is 60 - 90°C, and the highest value, 90°C, is herein adopted. The higher the temperature at which a drying process is performed, the more residual organic solvent contained in the ink of the pattern layer 32 can be scattered so that the in-mold decorating sheet 45 can be prevented from deteriorating due to residual organic solvent.

[0192] Also, the dimensional change rate herein refers to a rate (0.5/80, i.e. 0.6% as an example of the sixth embodiment of the present invention) of a dimensional change (within 0.5 mm as an example of the sixth embodiment of the present invention) due to elongation or shrinkage resulting when a sheet having a specified length dimension (80 mm as an example of the sixth embodiment of the present invention) at normal temperature

(20°C) is left under an ambient temperature (90°C as an example of the sixth embodiment of the present invention).

[0193] As to the setting of the dimensional change rate to within 0.6%, when in-mold decorated sheet articles were actually manufactured, the sizes of the manufactured in-mold decorating sheets were approximately 80 mm X 250 mm for an air-conditioner heater panel, 160 mm X 450 mm for a speed meter/fuel display panel, and 250 mm X 800 mm for a front grille. Therefore, with respect to the shortest dimension, 80 mm, out of these in-mold decorating sheets, there is a need for a printing registering accuracy of  $\pm 0.5$  mm in order to ensure that ordinary people do not have a bad feeling with regard to printing registering differences, hence a value of  $0.5/80$ , i.e., within 0.6%.

[0194] A thickness of the carrier sheet 34 is, preferably, within a range of 5 - 300  $\mu\text{m}$ . With a thickness under 5  $\mu\text{m}$ , the carrier sheet 34 could easily be cut by a tensile force of the printing machine; and with a thickness beyond 300  $\mu\text{m}$ , the carrier sheet 34 would be difficult to set up in a rotary printing press, thereby causing productivity to lower. Particularly, a carrier sheet 34 having a thickness of 15 - 50  $\mu\text{m}$  offers better workability with regard to laminating onto or separating from the substrate sheet 31, and thus is more preferable. Similarly, as compared with a case where pattern layer 32 is formed by printing directly onto substrate sheet 31 of the order of several hundreds  $\mu\text{m}$ , use of a carrier sheet 34 that is smaller in thickness than the substrate sheet enables printing and production by a multicolor rotary press, which leads to an improvement in mass productivity.

[0195] In order to facilitate separation of carrier sheet 34 from substrate sheet 31, or transfer of pattern layer 32 from carrier sheet 34 to substrate sheet 31 or a backing sheet, it is also advisable to execute a mold release treatment on a surface of the carrier sheet 34 so as to facilitate the separation.

[0196] However, with excessive separability, the carrier sheet 34 might be separated from the substrate sheet before formation of the pattern layer 32, or the pattern layer 32 might not be held on the carrier sheet 34 until the pattern layer 32 is transferred. Therefore,

the carrier sheet 34 is controlled so as to have an appropriate peeling strength of about 5 - 100 gf/cm.

[0197] More specifically, it is recommendable to adopt a heat lamination process, in which with a mold release layer formed on carrier sheet 34, the carrier sheet 34 and substrate sheet 31, after being laminated together, are bonded to each other by applying a pressure thereto while being heated on one side or both sides.

[0198] Next, a method for manufacturing an in-mold decorated article by using in-mold decorating sheet 45 having the above-described constitution is described.

[0199] First, the in-mold decorating sheet 45 is set to a surface of movable die 35, which is part of an injection mold, by virtue of clamp member 38 (see Fig. 21).

[0200] A concrete example of a manner of setting the in-mold decorating sheet 45 to the movable die 35 is as follows. A longer in-mold decorating sheet 45 is wound up on a roll shaft so as to be formed into a rolled state, and the resulting roll is placed at an upper portion of the movable die 35 so as to be movable integrally with the movable die 35. Then, the in-mold decorating sheet 45, while being wound out from the roll, is passed between the movable die 35, while retracted, and stationary die 36 so as to be wound up by a roll shaft of a film winding device which is set at a lower portion of the movable die 35 so as to be movable integrally with the movable die 35. Another example may be that a leaf-like in-mold decorating sheet 45 is set to a surface of the movable die 35 by a robot or human hand. For the setting of the in-mold decorating sheet 45 to the surface of the movable die 35, after the in-mold decorating sheet 45 is placed on the surface of the movable die 35, a position of the in-mold decorating sheet 45 relative to the surface of the movable die 35 is determined by a positioning sensor or the like, and the in-mold decorating sheet 45 may be pressed by clamp member 38 to the surface of the movable die 35.

[0201] Subsequently, the in-mold decorating sheet 45 is set to the surface of the movable die 35, and thereafter with use of vacuum suction holes 42 formed in the movable die 35, the in-mold decorating sheet 45 is vacuum-sucked along cavity-forming surface 37 of the movable die

35, by which the in-mold decorating sheet 45 is worked into a three-dimensional configuration along a recessed portion of the movable die 35, i.e., the cavity-forming surface 37 of cavity 43 (see Fig. 22). A concrete example is a method which includes steps of: heating the in-mold decorating sheet 45 to at least its softening point while the in-mold decorating sheet 45 set to the surface of the movable die 35, by utilizing a heating plate or the like inserted between the movable die 35 and the stationary die 36, and thereby softening the in-mold decorating sheet 45; closing the space between the recessed portion of the movable die 35 and the in-mold decorating sheet 45; and performing evacuation and vacuum suction through the vacuum suction holes 42 so that the in-mold decorating sheet 45 is put into close contact with the recessed-portion inner surface (cavity-forming surface 37) of the movable die 35. During a process of working the in-mold decorating sheet 45 into a three-dimensional configuration, or during a process of pressing and clamping the in-mold decorating sheet 45 by the clamp member 38, trimming of unnecessary portions of the in-mold decorating sheet 45 may be performed.

[0202] Instead of this method, before the in-mold decorating sheet 45 is set to the surface of the movable die 35, the in-mold decorating sheet 45 may preparatorily be worked into a desired configuration with a mold for three-dimensional working and molding, other than the movable die 35 and stationary die 36, and also trimmed into a desired configuration, and then the three-dimensionally worked in-mold decorating sheet 45 is fitted into the recessed portion of the movable die 35. As methods for three-dimensional working the in-mold decorating sheet 45, there are a vacuum molding method, an air-pressure forming method, a pressing method in which heated rubber is pressed against the in-mold decorating sheet, a press molding method, and the like. In addition, the trimming process may be performed concurrently with the process of working the in-mold decorating sheet into a three-dimensional configuration.

[0203] Next, with the movable die 35 clamped to the stationary die 36, molding resin 40 in a molten state is injected from the gate portion 39 of the stationary die 36 into cavity 43, and the molding resin 40 is solidified so that a resin molded article 41 is formed within the cavity 43

while the in-mold decorating sheet 45 is concurrently bonded integrally to a surface of the resin molded article 41 (see Fig. 23).

[0204]        Thereafter, the resin molded article 41 is removed from the movable die 35, and then unnecessary portions of the in-mold decorating sheet 45 bonded to the resin molded article 41 are removed (see Fig. 24). In the case where the in-mold decorating sheet 45 has preparatorily been trimmed into a desired configuration as described above, the step of removing the unnecessary portions of the in-mold decorating sheet 45 is unnecessary.

[0205]        The movable die 35 and the stationary die 36 as the injection mold are not particularly limited to the above embodiment. It is appropriate to use a mold which is made up of a movable die 35 and a stationary die 36 having a gate portion 39 for injecting the molding resin 40, where when the stationary die 36 and the movable die 35 are closed, a singularity or plurality of cavities 43 surrounded by the cavity-forming surfaces 37 of the stationary die 36 and the movable die 35 are formed. The in-mold decorating sheet 45 set within the cavities 43 formed by the movable die 35 and the stationary die 36 covers the cavity-forming surfaces 37. The cavities 43 may be provided as those which form a hole portion in the resin molded article 41. The recessed portion that forms the cavities 43 may be formed in either the stationary die 36 or the movable die 35. The movable die 35 or the stationary die 36 may have clamp member 38 for pressing and fixing the in-mold decorating sheet 45 around the recessed portion (see Figs. 21 to 23). The clamp member 38 may also be installed in the stationary die 36 or the movable die 35.

[0206]        The molding resin 40 is not particularly limited. Typical molding resins 40 to be used for interior automotive trims and exterior automotive trims are exemplified by polycarbonate resin, acrylonitrile butadiene resin, talc-containing polypropylene resin, and alloys of these resins.

[0207]        In addition, whereas the above description applies, as it is, to horizontal injection molding machines, the relationship between the stationary mold 36 and the movable mold 35 is reversed in the case of a vertical injection molding machine. Also, the mold of the injection molding machine is applicable not only to a two mold type but is also similarly applicable to a three mold type.

**(Seventh Embodiment)**

[0208] Next, a seventh embodiment of the present invention is described. This seventh embodiment is intended to solve a seventh issue, i.e., deficiency of opacifying power of a pattern layer.

5 [0209] The pattern layer, which is formed by coating, shows, in some cases, a color vision with high opacity and, in other cases, a color vision without high opacity, depending on differences in opacifying power among coloring materials for individual colors. The seventh issue is that when a pattern layer must be formed with a color vision quite different from a color of a backing sheet because of low opacifying power (for example, in the case of high-chroma  
10 yellow), there are some cases where a desired color vision cannot be obtained due to effects of the color of the backing sheet.

[0210] With respect to the seventh issue, the in-mold decorating sheet of the seventh embodiment of the present invention is so constituted that a second pattern layer 68 is formed between backing sheet 66 and pattern layer 63, as shown in Fig. 29.

15 [0211] More specifically, the pattern layer 63, which is formed by a general-purpose printing device or the like, shows, in some cases, a color vision with high opacity and, in other cases, a color vision without high opacity, depending on differences in opacifying power among coloring materials for individual colors.

[0212] When the pattern layer 63 must be formed with a color vision quite different from  
20 the color of the backing sheet 66 because of low opacifying power (for example, in the case of high-chroma yellow), there are some cases where a desired color vision cannot be obtained due to effects of the color of the backing sheet 66.

[0213] In such a case, the second pattern layer 68 is formed in order to enhance the opacifying power of the pattern layer 63.

25 [0214] The second pattern layer 68 may be formed either by coating or as a sheet.

[0215] The material of the second pattern layer 68 is, preferably, one which prevents vaporization and foaming, as in the case of the backing sheet 66.

[0216] The reason for this is that even in the case where the backing sheet 66 is not made of a material that prevents vaporization and foaming, the provision of the second pattern layer 68 that prevents vaporization and foaming makes it possible to suppress occurrence that a surface of the in-mold decorating sheet 61 appears in an orange-peel state even upon occurrence of vaporization and foaming of foaming components in the backing sheet 66. This could be attributed to the fact that it is only the backing sheet that vaporizes and foams, and the second pattern layer 68 acts to prevent gas generated from the backing sheet from reaching the pattern layer 63.

[0217] Concrete examples of such a material of the second pattern layer 68 are polyethylene resins, polypropylene resins, styrene resins, fire retardant ABS resins, or thermoplastic polybutadiene resins. More specifically, available as the material are polypropylene resin whose coefficient of water absorption is 0.03% or lower, polyethylene resin whose coefficient of water absorption is 0.01% or lower, polystyrene resin whose coefficient of water absorption is 0.07% or lower, fluoric resin whose coefficient of water absorption is 0.03% or lower, polyethylene terephthalate resin whose coefficient of water absorption is 0.15% or lower, polybutylene terephthalate resin whose coefficient of water absorption is 0.08% or lower, methacryl-styrene copolymer resin whose coefficient of water absorption is 0.15% or lower, fire retardant acrylonitrile butadiene-styrene copolymer resin (fire retardant ABS resin) whose coefficient of water absorption is 0.09% or lower, or thermoplastic polybutadiene resin whose coefficient of water absorption is 0.09% or lower.

[0218] A thickness of the second pattern layer 68 is, preferably, not less than 10  $\mu\text{m}$  in order to obtain opacity and vaporization/foaming prevention properties, and less than 200  $\mu\text{m}$  for prevention of visibility of trimming cross-section lines.

[0219] Although the molding resin is not particularly limited, the most typical molding resins for use in interior and exterior automotive trims or electrical appliances are polystyrene, acrylonitrile styrene copolymer resin, acrylonitrile butadiene-styrene copolymer resin, or polycarbonate resin and polypropylene resin and the like.



[0220] When polystyrene, acrylonitrile styrene copolymer resin, acrylonitrile butadiene-styrene copolymer resin, or polycarbonate resin is used as the molding resin, the primary material for the in-mold decorating sheet is, preferably, acrylic resin, styrenic resin (including styrenic elastomer resins), acrylonitrile butadiene-styrene base resin, thermoplastic polybutadiene base resin, polycarbonate base resin, or the like, in view of its recyclability after use. When polypropylene resin is used as the molding resin, the material of the in-mold decorating sheet is, preferably, polypropylene resin or polyethylene resin in view of its recyclability after use and its adhesion to the molding resin.

[0221] The most common method for three-dimensional working an in-mold decorating sheet is a vacuum molding method, which is a method in which the in-mold decorating sheet is heated to at least its softening point so as to be put into a soft and extendable state, and then vacuum-sucked and pulled in so as to come into close contact with an inner surface of a cavity of a mold for vacuum molding, and thus molded into a desired three-dimensional configuration.

[0222] Other three-dimensional working methods are an air-pressure forming method, a pressing method in which heated rubber is pressed against the in-mold decorating sheet, a press molding method, and the like.

[0223] After three-dimensional working of an in-mold decorating sheet, unnecessary portions of the in-mold decorating sheet, which are excluded from a decoration of a resin molded article, are removed by trimming. As trimming methods, usable are a method in which the in-mold decorating sheet is burned out and cut by irradiation of a laser beam, a method in which the in-mold decorating sheet is punched out by press working with a punching die prepared for trimming use, and the like.

[0224] The in-mold decorating sheet of a three-dimensional configuration, after performance of the trimming operation is fitted and set into an injection mold, and with the mold clamped, molding resin in a molten state is injected into a cavity and then cooled so

that a resin molded article is formed, while the in-mold decorating sheet is concurrently integrally bonded to a surface of the resin molded article.

[0225] In the foregoing embodiments, it is also possible to make the in-mold decorating sheet colored-looking by coloring a substrate sheet or backing sheet without providing any pattern layer.

[0226] More specifically, for example, Fig. 45 shows a state in which a backing sheet 3 adjacent to a substrate sheet 1 is a colored sheet of metallic red or the like, with black pigment 3m mixed therein. Also, Fig. 46 shows a state in which a backing sheet 3 adjacent to a substrate sheet 1 having a thickness of not more than 200  $\mu\text{m}$  is a colored sheet of metallic red or the like, with black pigment 3b mixed therein. Fig. 47 shows a state in which a backing sheet 3 is adjacent to a colored substrate sheet 1. Fig. 48 shows a state in which total thickness of the backing sheet and substrate sheet is not more than 200  $\mu\text{m}$  and in which a transparently colored pattern layer 2 is set between two colorless transparent substrate sheets 1A and 1B.

#### (Working Example 1)

[0227] An in-mold decorating sheet was manufactured under the following conditions.

[0228] On top of an acrylic film having a film thickness of 50  $\mu\text{m}$  and a surface pencil hardness of HB, a 5  $\mu\text{m}$  thick pattern layer was formed with the use of acrylic ink. On top of this pattern layer, with chlorinated polypropylene based adhesive ink interposed, a 200  $\mu\text{m}$  thick black polypropylene film (coefficient of water absorption: 0.01%; color:  $L^*=10$ ,  $a^*=3$ ,  $b^*=-5$ ), and a 150  $\mu\text{m}$  thick blackish brown polypropylene based film (coefficient of water absorption: 0.03%; with 60 parts by weight of EPDM and 15 parts by weight of talc blended on the basis of 100 parts by weight of polypropylene; color:  $L^*=10$ ,  $a^*=3$ ,  $b^*=-5$ ) were sequentially laminated, by which an in-mold decorating sheet having a thermal deformation temperature of 140°C was obtained. This in-mold decorating sheet exhibited a 200% elongation performance without being thermally decomposed when heated to 160°C, and had a Young's modulus of 85 kgf/mm<sup>2</sup> at normal temperature.

[0229] This sheet was vacuum-molded by heating to 160°C, trimmed by a laser, and inserted into an injection mold. Then polypropylene resin was injected at a molding temperature of 220°C, by which an in-mold decorated article was obtained.

**(Working Example 2)**

5 [0230] An in-mold decorating sheet was manufactured under the following conditions.

[0231] On top of a crystalline polypropylene film having a film thickness of 200  $\mu\text{m}$  and a surface pencil hardness of 2B, a 5  $\mu\text{m}$  thick pattern layer was formed with the use of 5  $\mu\text{m}$  urethane based ink. On top of this pattern layer, with chlorinated polypropylene based adhesive ink interposed, a 400  $\mu\text{m}$  thick black polypropylene film (coefficient of water absorption: 0.01%; color:  $L^*=8$ ,  $a^*=6$ ,  $b^*=-2$ ), was laminated, by which an in-mold decorating sheet having a thermal deformation temperature of 150°C was obtained. This in-mold decorating sheet exhibited a 130% elongation performance without being thermally decomposed when heated to 170°C, and had a Young's modulus of 70 kgf/mm<sup>2</sup> at normal temperature.

15 [0232] This sheet was vacuum-molded by heating to 170°C, trimmed by a laser, and inserted into an injection mold. Then, polypropylene resin was injected at a molding temperature of 220°C, by which an in-mold decorated article was obtained.

**(Working Example 3)**

[0233] An in-mold decorating sheet was manufactured under the following conditions.

20 [0234] On top of an acrylic film having a film thickness of 50  $\mu\text{m}$  and a surface pencil hardness of HB, a 5  $\mu\text{m}$  thick pattern layer was formed with the use of acrylic ink. On top of this pattern layer, with vinyl acetate based adhesive ink interposed, an intermediate sheet layer formed from a 100  $\mu\text{m}$  thick polystyrene film (coefficient of water absorption: 0.1%; color: yellow), and a 350  $\mu\text{m}$  thick black acrylonitrile butadiene-styrene film (coefficient of water absorption: 0.4%; color:  $L^*=7$ ,  $a^*=1$ ,  $b^*=1$ ) were sequentially laminated, by which an in-mold decorating sheet having a thermal deformation temperature of 110°C was obtained. This in-mold decorating sheet exhibited a 180% elongation

performance without being thermally decomposed when heated to 150°C, and had a Young's modulus of 140kgf/mm<sup>2</sup> at normal temperature.

[0235] This sheet was vacuum-molded by heating to 150°C, trimmed by a laser, and inserted into an injection mold. Then acrylonitrile butadiene-styrene resin was injected at a molding temperature of 230°C, by which an in-mold decorated article was obtained.

**(Working Example 4)**

[0236] An in-mold decorating sheet was manufactured under the following conditions.

[0237] On top of a noncrystalline polyester copolymer film having a film thickness of 60 μm, a 500Å metallic pattern layer formed of an evaporated aluminum film and a 2 μm adhesive layer formed of vinyl acetate based ink were formed sequentially.

[0238] Thereafter, with polyurethane based dry laminate adhesive ink interposed, a 200 μm thick black polypropylene film (coefficient of water absorption: 0.01%; color: L\*=10, a\*=3, b\*=5), and a 250 μm thick blackish brown polypropylene based film (coefficient of water absorption: 0.03%; with 60 parts by weight of EPDM and 15 parts by weight of talc blended on the basis of 100 parts by weight of polypropylene; color: L\*=10, a\*=3, b\*=5) were sequentially laminated, by which an in-mold decorating sheet having a thermal deformation temperature of 130°C was obtained. This in-mold decorating sheet exhibited a 160% elongation without being thermally decomposed when heated to 150°C, and had a Young's modulus of 90 kgf/mm<sup>2</sup> at normal temperature.

[0239] This sheet was vacuum-molded by heating to 160°C, trimmed by a laser, and inserted into an injection mold. Then polypropylene resin was injected at a molding temperature of 220°C, by which an in-mold decorated article was obtained.

**(Working Example 5)**

[0240] An in-mold decorating sheet was manufactured under the following conditions.

[0241] On top of a biaxially oriented polyethylene terephthalate film having a film thickness of 25  $\mu\text{m}$ , a four-color surprinted pattern layer having a registering accuracy within 0.2 mm, and a 2  $\mu\text{m}$  adhesive layer of vinyl acetate based ink were sequentially formed.

[0242] The ink layer side of this film was stacked on a polycarbonate film having a film thickness of 80  $\mu\text{m}$  and a surface pencil hardness of HB, and pressed by a 220°C thermal transfer roll, by which the pattern layer and the adhesive layer were transferred onto the polycarbonate film.

[0243] Further on top of this pattern layer, with vinyl acetate based adhesive ink interposed, an intermediate sheet layer formed by a 100  $\mu\text{m}$  thick polystyrene film (coefficient of water absorption: 0.1%; color: yellow), and a 250  $\mu\text{m}$  thick black acrylonitrile butadiene-styrene film (coefficient of water absorption: 0.4%; color:  $L^*=7$ ,  $a^*=1$ ,  $b^*=1$ ) were sequentially laminated, by which an in-mold decorating sheet having a thermal deformation temperature of 120°C was obtained. This in-mold decorating sheet exhibited a 160% elongation performance without being thermally decomposed when heated to 150°C, and had a Young's modulus of 160 kgf/mm<sup>2</sup> at normal temperature.

[0244] This sheet was vacuum-molded by heating to 150°C, trimmed by a laser, and inserted into an injection mold. Then acrylonitrile butadiene-styrene resin was injected at a molding temperature of 230°C, by which an in-mold decorated article was obtained.

[0245] Although the present invention has been fully described in connection with the preferred embodiments thereof with reference to the accompanying drawings, it is to be noted that various changes and modifications are apparent to those skilled in the art. Such changes and modifications are to be understood as included within the scope of the present invention as defined by the appended claims unless they depart therefrom.

## ABSTRACT OF THE DISCLOSURE

[0246] An in-mold decorating sheet is used in a manufacturing method of an in-mold decorated article. The method includes setting an in-mold decorating sheet into a mold for injection-molding. After clamping the mold, molding resin is injected and allowed to cool and solidify, by which all or part of the in-mold decorating sheet is integrally bonded to a surface of the molding resin. The in-mold decorating sheet comprises at least a substrate sheet and a backing sheet, and exhibits a tensile load at breakage of not less than 23 gf for prevention of breaking during the molding operation, as well as a tensile elongation at breakage of not less than 130% for elongation without breaking at a softening temperature.